



# Acrypol 2k paint

**Technical Specifications**  
 Date of issue: 19/02/2024  
 Version Number: 2th

## Ultradurable & everlasting 2k acrylic paint



ACRYPOL 2K PAINT, is a premium quality, highly durable 2-component acrylic paint, with powerful adhesion to a variety of difficult surfaces and everlasting resistance to permanent solar UV radiation and adverse weather conditions such as: constant humidity, sea water, hail, snow, frost, exhaust gases and chemical pollutants. It doesn't yellow, peel, crack or pluck and keeps unchanged its original shade and sheen for a very long time. The final film it forms is distinguished for its high hardness and elasticity, but also for its unique resistance to oils, greases, solvents, detergents, and chemicals. It is available in gloss, satin and matt finishes and can be tinted in an unlimited number of shades. Ideal product for coastal and mountainous areas.

### Fields of application

It is applied to wood, iron, stone, aluminum, concrete, ceramics and generally on any difficult surface. Ideal for painting and protecting external surfaces where an everlasting finish is required with excellent resistance to adverse weather conditions and permanent solar radiation. Also suitable for indoor use.

### Surface preparation

The surfaces must be completely dry, clean and free from dust, oil, grease, loose materials, flaking paints or varnishes and sanded with a suitable abrasive paper. To prepare wooden surfaces, prime with VERNILAC's ACRYPOL 2K PRIMER. On metal surfaces, use VERNILAC's 2-component epoxy primer DUREPOX METAL PRIMER. By using DUREPOX METAL PRIMER, you achieve top anti-rust protection for up to 10 years. For non-ferrous surfaces, such as: aluminum, galvanized steel, copper, zinc, etc., use VERNILAC's 2-component phosphating primer WASH PRIMER. Application to bamboo requires very fine sanding with Freecut Grit 240 abrasive.

### Thinning

Up to 12% with polyurethane thinner 4099, P2 or P3, depending on temperature. For industrial use only and spray-gun or airless spray application, thin 20-30% with VERNILAC 4099, P2 or P3 thinner, depending on - temperature.

### Physical / Technical Characteristics

#### WHITE SATIN

Viscosity	20 ± 2 Poise
Density	1,28 ± 0,02 kg/lit (ISO 2811.01,20°C)
Gloss level	40 ± 5 @60 °C

#### WHITE GLOSS

Viscosity	60 ± 5 DIN No.6 at 25°C
Density	1,27 ± 0,02 kg/lit (ISO 2811.01,20°C)
Gloss level	100 @60 °C

#### WHITE MATT

Viscosity	70 ± 5 DIN No.6 at 25°C
Density	1,33 ± 0,02 kg/lit (ISO 2811.01,20°C)
Gloss level	18 ± 3 @60 °C

### Mixing

2 parts A' component with 1 part B' component (hardener) by volume. For industrial use only, adding 20% more hardener (mixing ratio 2:1,2) increases the elasticity of the coating and its service life.

### Workability of mixture – pot life

3-4 hours at a temperature of 30°C. At higher temperatures the workability of the mixture decreases.

### Application

Before application, it is always necessary to stir the two components separately. Then, mix the two components of ACRYPOL 2K PAINT and stir well until the mixture is completely homogenized. After pretreatment and mixing is complete, apply with brush or roller, one coat of ACRYPOL 2K PAINT diluted up to 12% with polyurethane thinner 4099, P2 or P3. For industrial use and application via spray-gun or airless, thin 20%-30% with polyurethane thinner 4099, P2 or P3. After at least 6 hours, apply a second coat of ACRYPOL 2K PAINT. Time from hand to hand at least 6 hours. The surface is ready for use after 24 hours, while it fully acquires its mechanical and chemical resistance in 7 days.



# Acrypol 2k paint

**Technical Specifications**  
Date of issue: 19/02/2024  
Version Number: 2th

## Drying - Repainting

Drying at a temperature of 25°C: Touch dry: 45 minutes. Recoat: after 6 hours and no later than 24 hours. When repainting after 24 hours, sanding is obligatory. Full hardening of the paint is achieved in 7 days. In low temperatures or conditions of increased humidity, drying times are extended. Avoid application at temperatures below 5°C and above 35°C.

## Consumption

Approximately 12-14 m<sup>2</sup>/L, per layer, on properly prepared surfaces, for a dry film thickness of 60-100µm.

## Shades

It is available in white gloss, satin and matt and can be tinted in an unlimited number of shades through the industrial color creation system COLOR CREATIONS by VERNILAC.

## Storage

The factory-sealed package is kept for at least 6 months in a shaded and cool environment, at temperatures ranging from 5°C to 35°C. After application, tightly seal the container and store in suitable conditions.

## Cleaning tools

Immediately after use, clean tools with ACETONE or VERNILAC's polyurethane solvent 4099. Do not pour washing liquids into water courses.

## Volatile organic compounds (VOC)

The maximum EU limit value (Directive 2004/42/CE) for this product [Category A/j "Two-pack reactive performance coatings for specific end use such as floors", Type SB] is 500 g/l (2010). This product contains maximum 499 g/l VOC (ready for use).

## Packaging

WHITE GLOSS	0,5 lt	1 lt	4 lt
WHITE SATIN	0,5 lt	1 lt	4 lt
WHITE MATT	0,5 lt	1 lt	4 lt
HARDENER	0,25 lt	0,5 lt	2 lt

## Safety information

Read the label before use. For detailed instructions - precautions, consult the Product Safety Data Sheet. Poison Information Centre: (+30) 210 77 93 777.

**THE PRODUCT IS INTENDED FOR PROFESSIONAL USE ONLY**



All the information provided in this technical data sheet is the result of the scientific knowledge of the company's personnel and the practical experience in product application. This document doesn't express or imply a guarantee as the company cannot control and bears no responsibility for the conditions and the manner of application, the adjustment and the modification of the product when used by the customer. The customer must confirm by his own means that the product is suitable for the intended use. The current version of technical data sheet withdraws all previous versions for this product.

