

Aqualasur MC 321

Technical Specifications
Date of issue: 17/07/2025
Version Number: 3rd

Water-Based, Single-Component Filling and Insulating Primer



- Ideal as an intermediate coat for wooden surfaces mainly for exterior use.
- Very good penetration and wood pores filling.
- Insulates from wood oil extracts, fills very well the pores, easy for sanding.
- Ideal for the hard and sensitive parts of the wooden surfaces such as joints, edges, router gaps, etc. on doors, windows and wooden profiles.
- Odorless and user friendly.
- Can be tinted in many various colors.
- Applied by spray (spray gun - airless), roller or brush.

Thinning

0-5% with clean water

Coverage

150-200 ml/ m².

Drying - Recoating

Approximately 60 minutes in normal weather conditions (23°C / 50% relative moisture). After 6-10 hours for further applications of finishing products.

Physical / Technical Characteristics

Viscosity	110±10 KU
Density	1,04±0,015 kg/lit (ISO 2811.01, 20°C)

Storage

It can be stored for 12 months in factory sealed containers, in a cool, dry place and temperatures ranging from 5°C to 35°C.

Left over product must be stored in similar conditions and in tightly resealed containers.

Clean up

Clean up tools and equipment with water, immediately after use. If needed, use soap or a household detergent solution.

Do not empty waste water into drains or watercourses.

Volatile organic compounds (VOC)

The maximum EU limit value (Directive 2004/42/EC) for this product (Category A/f "Interior and exterior minimal build wood stains", Type WB) is 130 g/l (2010). This product contains maximum 129 g/l VOC (ready for use).

Packaging

Colorless	750 ml.	3 lt.	10 lt.
-----------	---------	-------	--------

Safety information

Read the label before use. For detailed instructions - precautions, consult the Product Safety Data Sheet.