




Decocryl

Technical Specifications
 Date of issue: 07/11/2025
 Version Number: 7th

General purpose acrylic cement paint suitable for exterior use and frequent paint freshening up



DECOCRYL is an economical acrylic paint for general use in outdoor surfaces made of concrete, plaster, bricks, cement board and wood with good resistance properties to weather conditions and high alkalinity. It represents the most economical solution for the protection and decoration of all exterior settings that need frequent paint freshening up such as large scale public works, schools, hotels, hospitals, factories. It provides strong adhesion and combines high coverage, whiteness, good spreading rate, very good leveling and ease of application. DECOCRYL dries fast and creates a nice matt surface.

Surface preparation

Surface must be clean, dry and free from dirt, grease, wax, salts, mildew and scaling paint. For filling cracks, nail holes or surface imperfections use VERNILAC's Acrylic Masonry Putty SPATOCRYL or SPATOCRYL ELASTIC when flexible and elastic filler is required. On new surfaces prime with VERADUR A-100, VERNILAC's all-purpose 100% Acrylic Primer, diluted 200-300% with clean water. On highly porous surfaces or when repainting surfaces that were previously painted with lime paints, poor quality paints or poorly adhesive coatings, scrape off all loose and flaking paint and prime with VERNILAC's Solvent Based DUROCOAT PRIMER, diluted 100% with WHITE SPIRIT. On old surfaces with light porosity held in sound condition without adhesion problems, whether prime with VERADUR A-100, VERNILAC's all-purpose 100% Acrylic Primer, diluted 300-400% with clean water or paint directly.

Thinning

10-15% with clean water.

Physical / Technical Characteristics

Viscosity	115±3 KU (ASTM D 562, 20°C)
Density	1,57-1,58±0,015 kg/lit depending of shade (ISO 2811.01, 20°C)

Application

Stir thoroughly and occasionally during use. Apply by brush, roller, spray or airless two coatings of DECOCRYL on every new or repainted exterior surface made of concrete, plaster, cement board, wood, etc. Do not apply when air and surface temperatures are below 5°C, above 40°C and/or humidity level is above 80%.

Drying - Recoating

Touch dry after 60 minutes. Recoat after 3 hours. Under cooler or humid conditions, allow longer times.

Coverage

Approximately 12-14 m²/lt per layer, on a properly prepared surface.

Color shades

Available in white. The bases of DECOCRYL can be tinted in an unlimited number of light and dark shades with VERNILAC's COLOR CREATIONS Tinting System.

Storage

12 months, if stored in factory sealed containers, in a cool, dry place and temperatures ranging from 5°C to 40°C. Left over paint must be stored, in tightly sealed containers and temperatures ranging from 5°C to 40°C.

Clean up

Clean up tools and equipment with water, immediately after use. If needed, use soap or a household detergent solution. Do not empty waste water into drains or watercourses.

Volatile organic compounds (VOC)

The maximum EU limit value (Directive 2004/42/CE) for this product [Category A/c "Exterior walls of mineral substrate", Type WB] is 40 g/l (2010). This product contains maximum 39 g/l VOC (ready for use).

Packaging

White	3 lt.	9 lt.	15 lt.
Base P	3 lt.	9 lt.	

Safety information

Read the label before use. For detailed instructions - precautions, consult the Product Safety Data Sheet. Poison Information Centre: (+30) 210 77 93 777.



All the information provided in this technical data sheet is the result of the scientific knowledge of the company's personnel and the practical experience in product application. This document doesn't express or imply a guarantee as the company cannot control and bears no responsibility for the conditions and the manner of application, the adjustment and the modification of the product when used by the customer. The customer must confirm by his own means that the product is suitable for the intended use. The current version of technical data sheet withdraws all previous versions for this product.

