



Kilrust

Technical Specifications
Date of Issue: 17/07/2025
Version Number: 5th

Powerful Rust Remover for Metal Surfaces, Marble and Mosaics



Color

Colorless

Storage

Shelf life: 12 months (in factory-sealed packaging). Store in a shaded, cool environment at temperatures between 5°C and 40°C. After use, seal the container tightly and store under appropriate conditions

Packaging

Colorless	900 ml
-----------	--------

Safety Information

Read the label before use. For detailed instructions and precautions, consult the product's Safety Data Sheet.

Poison Control Center: +30 210 77 93 777.

A highly effective rust remover for metal surfaces, marble, mosaics, etc. Water-soluble.

It neutralizes rust by converting it into iron phosphate.

Creates stable, compact metal surfaces with enhanced mechanical and physical resistance, ready for anti-rust protection and final decorative finishing with water- or solvent-based varnish paints.

Thinning

Can be diluted up to 50% by volume with clean water.

Physical/Technical Characteristics

Density	1,08±0,01 kg/lit depending on the shade (ISO 2811.01, 20°C)
---------	---

Application

Preparation: Remove loose rust from the surface before applying. Metal surfaces: For heavy rust, apply undiluted using a brush in two or three layers. For light rust, one coat is usually sufficient and may be diluted up to 50% with water.

After cleaning, rinse the surface thoroughly with plenty of water, then apply an anti-rust primer.

Marble & Mosaics: Dilute more than 50% and apply locally on rust spots with a sponge or absorbent cloth.

IMMEDIATELY rinse the surface thoroughly with plenty of water.

WARNING! Rinsing with clean water must be done immediately to avoid surface dullness.

Drying Time

Apply directly onto rust on dry and clean surfaces, free from loose material, dust, oils, etc. Dries within 2-3 hours, changing color from reddish-brown to off-white



All information provided in these technical specifications is the result of the company's scientific knowledge and practical experience in applying the product. This document does not constitute a warranty, as the company cannot control or be responsible for the conditions and method of application, adjustment, and processing of the product by the customer. The customer must independently verify that the product is suitable for the intended application. The current version of the technical specifications supersedes all previous versions for this product.



Σελίδα 1 από 1 / Page 1 from 1