

Parquet Lx 860

Technical Specifications
 Date of issue: 07/11/2025
 Version Number: 11th

Two pack polyurethane varnish for floors



PARQUET LX 860 is a high quality, two component, polyurethane based clear varnish ideal for application on wooden floors (parquets). It is a hard wearing, long life finish, with superior gloss retention and exceptional resistance properties against friction, scratching, household detergents, chemicals and solvents. It is applied easily, smoothly and evenly, providing a superb finish that gives long term protection and beauty that lasts.

Product information

Use on: Interior wooden floors (parquets). Application: Roller, brush or spatula when applied in building interiors. Spray-gun or airless, when applied in industrial applications. Mixing proportion: 1 part of PARQUET A' to 1 part of PARQUET B', by volume. Thinning: It is ready for use and no thinning is required when applied by roller, brush or spatula. If necessary, thin up to 6% by volume with VERNILAC's thinner 3800 for the Gloss varnish and up to 6% by volume with VERNILAC's thinner 4800 for the Satin and Matt finishes.

In industrial applications, when LX 860 Gloss is applied by spray-gun or airless, thin 30-35% by volume, using VERNILAC's thinner 3800. When LX 860 Satin and Matt is applied by spray-gun or airless, only for industrial applications, thin 30-35% by volume, using VERNILAC's thinner 4800. Pot life: 4-6 hours.

ATTENTION !!! The mixture of PARQUET A+B must be used within 4-5 hours. Coverage: 8-9 m² per litre, on a properly prepared surface. Drying times on a day of around 25°C: Touch dry: 4 hrs. Recoat: The next day. Under cooler or humid conditions, allow longer times. Avoid application in temperature below 5°C or above 34°C.

Physical / Technical Characteristics

Viscosity	18±1 sec (CF4, 25°C)
Density	1,055±0,005 kg/lit (20°C) (A Component)

Surface preparation

Ensure that the wooden surface is completely dry, free from grease, dust, dirt and poorly adhesive materials. On wooden floors made by regular timber, apply one coat of VERNILAC's PARQUET PRIMER 3700 undiluted. On wooden floors made by tropic timber, always use special isolating primers.

Application

Prior to mixing, always stir well each component separately. Mix equal quantities of component A' with component B', by volume, stir well to homogenize the mixture and apply one full coat of PARQUET LX 860. After drying, sand smoothly with a suitable abrasive paper (FREE CUT No.240-280), dust down and apply a second full coat. Clean up equipment immediately after use, with VERNILAC's ACETON or polyurethane thinner 3800. Always keep the containers tightly closed and especially PARQUET B' component, because its content will be damaged in presence of air and humidity.

Volatile organic compounds (VOC)

The maximum EU limit value (Directive 2004/42/CE) for this product [Category A] "Two-pack reactive performance coatings for specific end use such as floors", Type SB] is 500 g/l (2010). This product contains maximum 499 g/l VOC (ready for use).

Packaging

Gloss A	1/1	2,5/1	5/1
Gloss B	1/1	2,5/1	5/1
Satin A	1/1	2,5/1	
Satin-Matt B	1/1	2,5/1	
Matt A	1/1	2,5/1	
Satin-Matt B	1/1	2,5/1	

Safety information

Read the label before use. For detailed instructions - precautions, consult the Product Safety Data Sheet. Poison Information Centre: (+30) 210 77 93 777.



All the information provided in this technical data sheet is the result of the scientific knowledge of the company's personnel and the practical experience in product application. This document doesn't express or imply a guarantee as the company cannot control and bears no responsibility for the conditions and the manner of application, the adjustment and the modification of the product when used by the customer. The customer must confirm by his own means that the product is suitable for the intended use. The current version of technical data sheet withdraws all previous versions for this product.